

NEW HASE *Technologies* **PERFORMA™ V 343 Polymer**
Specialty Polymers

INCI NAME: Synthetic Wax

Characteristic	Test method	Current specification
Color	ASTM D1500 Modified	0.5 max
Softening point (°F)	ASTM D36 Modified	105.0 ± 15.0
Viscosity at 210°F (99°C)	ASTM D3236 Modified	130 ± 40.0
Penetration at 77°F (25°C), dmm	ASTM D1321 Modified	30.0 ± 20.0
Flash point by Pensky-Martens	ASTM D93 Modified	300 min

These specifications may be superseded as per our specification review and revision procedure.

Because it has become common for purchasers of our products to file patents for specific end uses of our products, Baker Hughes advises its customers to research their particular end use for possible intellectual property issues with respect to third party patents.

Effective Date: 01/26/2006

Baker Hughes
P.O. Box 669
Barnsdall, OK 74002 USA
Tel: +1.918.847.2522
Fax: +1.918.847.3012

PERFORMA is a trademark of Baker Hughes Incorporated.

Disclaimer of Liability: This information is provided for general information purposes only and is believed to be accurate as of the date hereof; however, Baker Hughes Incorporated and its affiliates do not make any warranties or representations of any kind regarding the information and disclaim all express and implied warranties or representations to the fullest extent permissible by law, including those of merchantability, fitness for a particular purpose or use, title, non-infringement, accuracy, correctness or completeness of the information provided herein. All information is furnished "as is" and without any license to distribute. The user agrees to assume all liabilities related to the use of or reliance on such information. BAKER HUGHES INCORPORATED AND ITS AFFILIATES SHALL NOT BE LIABLE FOR ANY DIRECT, INDIRECT, SPECIAL, PUNITIVE, EXEMPLARY OR CONSEQUENTIAL DAMAGES FROM ANY CAUSE WHATSOEVER INCLUDING BUT NOT LIMITED TO ITS NEGLIGENCE.

