

PERFORMA™ V103 Polymer

Characteristic	Test Method	Current Specification
Color, ASTM	ASTM D1500 Modified	0.5 max
Softening Point (°F)	ASTM D36 Modified	155.0 – 175.0
Softening Point (°C)	ASTM D36 Modified	68.3 – 79.4
Viscosity @ 210°F (98.9°C)	ASTM D3236 Modified	250.0 – 440.0
Penetration @ 77°F (25°C)	ASTM D1321 Modified	3.0 – 7.0
Flash (COC), °F	ASTM D92 Modified	450.0 min
Flash (COC), °C	ASTM D92 Modified	232.2 min
Color, Gardner	ASTM D1544 Modified	Record Only

These specifications may be superseded as per our specification review and revision procedure.

Because it has become common for purchasers of our products to file patents for specific end uses of our products, NuCera Solutions advises its customers to research their particular end use for possible intellectual property issues with respect to third party patents.

Effective Date: 10/20/2020

Disclaimer of Liability: This information is provided for general information purposes only and is believed to be accurate as of the date hereof; however, NuCera Solutions LLC and its affiliates do not make any warranties or representations of any kind regarding the information and disclaim all express and implied warranties or representations to the fullest extent permissible by law, including those of merchantability, fitness for a particular purpose or use, title, non-infringement, accuracy, correctness or completeness of the information provided herein. All information is provided "as is" and without any license to distribute. The user agrees to assume all liabilities related to the use of or reliance on such information. NUCERA SOLUTIONS LLC AND ITS AFFILIATES SHALL NOT BE LIABLE FOR ANY DIRECT, INDIRECT, SPECIAL, PUNITIVE, EXEMPLARY, OR CONSEQUENTIAL DAMAGES FROM ANY CAUSE WHATSOEVER INCLUDING BUT NOT LIMITED TO ITS NEGLIGENCE.

REFERENCE No. 25272015