

PERFORMA™ SW-76 synthetic wax

INCI: synthetic wax

Characteristic	Test Method	Typical Properties
Melt Point (°F)	ASTM D127 Modified	167.0 – 174.0
Melt Point (°C)	ASTM D127 Modified	74.0 – 78.9
Viscosity @ 300°F (148.9°C), cPs	ASTM D3236 Modified	2.0 – 6.0
Penetration @ 77°F (25°C), dmm	ASTM D1321 Modified	5.0 – 12.0
Color, Saybolt	ASTM D156 Modified	5.0 – 25.0

These specifications may be superseded as per our specification review and revision procedure.

Because it has become common for purchasers of our products to file patents for specific end uses of our products, NuCera Solutions advises its customers to research their particular end use for possible intellectual property issues with respect to third party patents.

Effective Date: 12/2/2022

Disclaimer of Liability: This information is provided for general information purposes only and is believed to be accurate as of the date hereof; however, NuCera Solutions LLC and its affiliates do not make any warranties or representations of any kind regarding the information and disclaim all express and implied warranties or representations to the fullest extent permissible by law, including those of merchantability, fitness for a particular purpose or use, title, non-infringement, accuracy, correctness or completeness of the information provided herein. All information is provided "as is" and without any license to distribute. The user agrees to assume all liabilities related to the use of or reliance on such information. NUCERA SOLUTIONS LLC AND ITS AFFILIATES SHALL NOT BE LIABLE FOR ANY DIRECT, INDIRECT, SPECIAL, PUNITIVE, EXEMPLARY, OR CONSEQUENTIAL DAMAGES FROM ANY CAUSE WHATSOEVER INCLUDING BUT NOT LIMITED TO ITS NEGLIGENCE.